



# Fraunhofer

## TESTED<sup>®</sup> DEVICE

VERMOP Salmon GmbH  
White Magic cleanroom  
**Report No. VE 1909-1142**

DUPLICATE

Statement of  
Qualification

Single product  
Particle Emission

Customer	VERMOP Salmon GmbH Zeppelinstrasse 24 82205 Gilching Germany
Component tested	
Category:	Materials
Subcategory:	Consumables
Product name:	Mop White Magic cleanroom (manufacturing date: 4/2019; material: 100 % polyester; color: white; article number: 1447485PES; charge number: 049; dimensions: 40 cm)

Random sampling of particle emissions (airborne)

Standards/Guidelines:	ISO 14644-1, -14; VDI 2083 Part 9.2, without 24-hour running-in period The norms stated generally refer to the version valid at the time of the tests.
Test devices:	Optical particle counter: LasAir II 110 with measuring ranges $\geq 0.1 \mu\text{m}$ , $\geq 0.2 \mu\text{m}$ , $\geq 0.3 \mu\text{m}$ , $\geq 0.5 \mu\text{m}$ , $\geq 1.0 \mu\text{m}$ and $\geq 5.0 \mu\text{m}$
Test environment parameters:	<ul style="list-style-type: none"><li>Cleanroom Air Cleanliness Class (according to ISO 14644-1):..... ISO 1</li><li>Airflow velocity:.....0.45 m/s</li><li>Airflow pattern:..... vertical laminar flow</li><li>Temperature: .....22 °C <math>\pm</math> 0.5 °C</li><li>Relative humidity: ..... 45 % <math>\pm</math> 5 %</li></ul>
Test procedure parameters:	Test bench according to ISO 9073-10: <ul style="list-style-type: none"><li>Sample clamping position:..... flat</li><li>Length between clamping points: ..... 230 mm</li><li>Motion cycle:<ul style="list-style-type: none"><li>Linear compression s:..... 120 mm</li><li>Torsion: ..... 180 °</li></ul></li><li>Cycle time t: .....1 s</li><li>Sampling chamber:.....none</li><li>Duration of stress applied to test piece: ..... 100 min</li><li>Distance between particle counting probe and test piece:..... 30 mm</li></ul>

Test result / Classification

When operated in a dry state using the given test parameters, the mop White Magic cleanroom is suitable for use in cleanrooms up to the following Air Cleanliness Class according to ISO 14644-1:

Test parameter(s)	Air Cleanlines Class
Linear compression = 120 mm Torsion = 180 ° Cycle time t = 1 s	7
Overall result	7

This is consistent with an ISO-ACP<sub>c</sub> Class 7 from VDI 2083 Part 9.2.

Please note: Transport damage, incorrect installation and aging behavior etc. can influence the test result.

The measuring devices used for the qualification tests are calibrated at regular intervals; their results can be traced back to national and international standards. In cases where no national standards exist, the test procedure implemented complies with the technical regulations and norms applicable at the time of the test. The relevant documentation can be viewed on request at any time.

Detailed information and parameters of the test environment can be found in the Fraunhofer IPA test report.

Fraunhofer Institute for Manufacturing Engineering and Automation IPA	VE 1208-609 Report No. first document	Stuttgart, April 26, 2013 Place, date of first document issued
Department of Ultraclean Technology and Micromanufacturing	VE 1909-1142 Report No. current document	Stuttgart, October 21, 2019 Place, current date
Nobelstrasse 12 70569 Stuttgart Germany	on behalf of Dr.-Ing. Frank Bürger, Project Manager Fraunhofer IPA	